

**CEN/CEN WS XXX**

Date: 2026-02

**Draft CWA XXXXX: XXXX**

Workshop: XXX

**CEN Workshop BIOUPTAKE — Technical and ecotoxicological analysis of  
biobased materials**

CCMC will prepare and attach the official title page.

<b>Contents</b>		Page
<b>Foreword</b> .....		<b>3</b>
<b>Introduction</b> .....		<b>4</b>
<b>1</b>	<b>Scope</b> .....	<b>5</b>
<b>2</b>	<b>Normative references</b> .....	<b>5</b>
<b>3</b>	<b>Terms and definitions</b> .....	<b>5</b>
<b>4</b>	<b>Symbols and abbreviations</b> .....	<b>6</b>
<b>5</b>	<b>Preparation of solutions, elutriates, and leachates</b> .....	<b>6</b>
<b>5.1</b>	<b>Epoxy resins</b> .....	<b>6</b>
<b>5.2</b>	<b>Bio-based fibers and polymers in the form of pellets</b> .....	<b>7</b>
<b>5.3</b>	<b>Intermediate composite formats</b> .....	<b>7</b>
<b>6</b>	<b>Ecotoxicological assays</b> .....	<b>7</b>
<b>6.1</b>	<b>72-h growth inhibition test <i>Raphidocelis subcapitata</i></b> .....	<b>7</b>
<b>6.2</b>	<b>7-days <i>Lemna minor</i> Growth Inhibition test</b> .....	<b>8</b>
<b>6.3</b>	<b>24-h acute test with <i>Brachionus calyciflorus</i></b> .....	<b>8</b>
<b>6.4</b>	<b>48-h Immobilisation test with <i>Daphnia magna</i></b> .....	<b>8</b>
<b>6.5</b>	<b>96-h Fish Embryo Acute Toxicity test with <i>Danio rerio</i></b> .....	<b>9</b>
<b>Annex A (informative) Calibration curve</b> .....		<b>11</b>
<b>Bibliography</b> .....		<b>12</b>

## Foreword

This CEN Workshop Agreement (CWA XXXX:YYYY) has been developed in accordance with the CEN-CENELEC Guide 29 “CEN/CENELEC Workshop Agreements — A rapid way to standardization” and with the relevant provisions of CEN/CENELEC Internal Regulations - Part 2. It was approved by the Workshop CEN Workshop BIOUPTAKE — Technical and ecotoxicological analysis of biobased materials, the secretariat of which is held by Asociación Española de Normalización, UNE consisting of representatives of interested parties on 2025-12-03, the constitution of which was supported by CEN following the public call for participation made on 2025-10-10. However, this CEN Workshop Agreement does not necessarily include all relevant stakeholders.

The final text of this CEN Workshop Agreement was provided to CEN for publication on YYYY-MM-DD.

Results incorporated in this CWA received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 101057049.

The following organizations and individuals developed and approved this CEN Workshop Agreement:

- UNIVERSITY AVEIRO, Isabel Lopes
- UNIVERSITY AVEIRO, Catia Venancio
- AITIIP, Leyre Hernandez
- AITIIP, Alejandro Marques
- CETEXBEL, Ruben Geerinck
- CETEXBEL Robbe De Bisschop
- EUROFINS ECOTOXICOLOGIE FRANCE, Eloïse RENOUF
- MOSES PRODUCTOS S.L., Julio Vidal

Attention is drawn to the possibility that some elements of this document may be subject to patent rights. CEN-CENELEC policy on patent rights is described in CEN-CENELEC Guide 8 “Guidelines for Implementation of the Common IPR Policy on Patent”. CEN shall not be held responsible for identifying any or all such patent rights.

Although the Workshop parties have made every effort to ensure the reliability and accuracy of technical and non-technical descriptions, the Workshop is not able to guarantee, explicitly or implicitly, the correctness of this document. Anyone who applies this CEN Workshop Agreement shall be aware that neither the Workshop, nor CEN, can be held liable for damages or losses of any kind whatsoever. The use of this CEN Workshop Agreement does not relieve users of their responsibility for their own actions, and they apply this document at their own risk. The [CEN Workshop Agreement should not be construed as legal advice authoritatively endorsed by CEN/CENELEC.

## Introduction

CEN/CENELEC Workshop Agreement is a result of the European R&I project Bio-Uptake funded by the European Union under the grant agreement number 101057049.

The transition to a circular bioeconomy is a cornerstone of the European Green Deal, aiming to replace fossil-based materials with sustainable bio-based alternatives while minimizing environmental impacts. In 2022, bio-based plastics production in Europe reached approximately 2.2 million tonnes, representing 1.6% of total plastics but projected to grow to 5.6 million tonnes by 2027 (16% market share), driven by policies like the Renewable Energy Directive and Circular Economy Action Plan. However, rapid innovation in bio-based materials—such as bioplastics (e.g., PLA, PHA), fibers, and composites—raises concerns about potential ecotoxicity from additives, impurities, or degradation products, necessitating robust safety assessments under REACH and CLP regulations.

Bio-based products must undergo life-cycle ecotoxicological evaluation to verify environmental safety, including leachates/elutriates testing for aquatic hazards via standardized batteries (e.g., OECD TGs 201, 202, 203, 236). Yet, fragmented protocols across innovation stages—from raw feedstocks (lignocellulose, algae) to intermediates (pellets, composites) and end-products—hinder consistent hazard characterization. Existing standards like EN 16785 (bio-based content) and EN 13432 (compostability) focus on physicochemical properties but lack harmonized ecotoxicity roadmaps.

The BIOUPTAKE project addresses this by developing a roadmap for preparing diverse bio-based substances and materials for ecotoxicity testing along the value chain. This includes extraction protocols (e.g., DIN 38414-4 elutriates, CEN/TS 15863 leachates), solvent limits ( $\leq 0.01\%$  DMSO per OECD), and multispecies assays representing multiple trophic levels (*Raphidocelis subcapitata*, *Daphnia magna*, *Danio rerio* embryos). By integrating technical preparation with hazard profiling, BIOUPTAKE ensures bio-products comply with EU sustainability criteria, supporting claims under the Sustainable Products Initiative and preventing microplastic/ecotoxin releases.

This CWA describes BIOUPTAKE methodologies, implemented by the consortium, for the characterization of the freshwater ecotoxicity of bio-based developed substances, materials and intermediate composites. This complementary approach will allow materials and products to be validated in terms of environmental requirements for their marketing.

This CWA will not define requirements related to safety aspects.

## 1 Scope

This CWA establishes a tests methodology for the ecotoxicity characterization of bio-based substances and materials and benchmark them with the corresponding fossil-based that are currently marketed.

The characterization process described in this CWA can be applied to bio-based epoxy resins; bio-based fibers from wood and carbon materials, bio-based polymers in the form of pellets and intermediate bio-based composite formats.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

CEN/TS 15863:2015, *Characterisation of waste — Leaching behaviour test for basic characterisation — Dynamic monolithic leaching test with periodic leachant renewal, under fixed test conditions*

DIN 38414-4:1984, *Methods for the examination of water, wastewater and sludge; sludge and sediments (group S); determination of leachability by water (S 4)*

ISO 19827:2015, *Water quality — Determination of chronic toxicity to *Brachionus calyciflorus* — Short-chronic protocol*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp/>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### **elutriate**

aqueous solution obtained after adding water to a solid substance (e.g., sediment, tailings, drilling mud, or dredging spoil), shaking the mixture, then centrifuging or filtering it or decanting the supernatant

### 3.2

#### **solution - A**

liquid or solid phase containing more than one substance, when for convenience one (or more) substance, which is called the solvent, is treated differently from the other substances, which are called solutes. When, as is often but not necessarily the case, the sum of the mole fractions of solutes is small compared with unity, the solution is called a dilute solution. A superscript attached to the symbol for a property of a solution denotes the property in the limit of infinite dilution. (Orange Book, 2nd ed., p. 83)

## 4 Symbols and abbreviations

1,6-H	1,6-Hexanediamine
4,4'-D	4,4'-Dithiodiamine
4-AFD	4-aminophenyl difsulfide
CF	Carbon Fiber
CYS	Cystamine
DGEBA	Diglycidylether of bisphenol-A
DGEVA	Diglycidylether of vanillyl alcohol
DMSO	Dimethyl Sulfoxide
PA	Polyamide
PCL	Polycaprolactone
PHTE	Phloroglucinol trisepox
PLA	Polylactic acid
WF	Wood Fiber

## 5 Preparation of solutions, elutriates, and leachates

### 5.1 Epoxy resins

Stock solutions of epoxy resins should be prepared by directly dissolving the resins in the standard test medium designated for the ecotoxicity assay with each target freshwater species. Special precautions are required during resin handling to prepare these stock solutions, as certain resins are oxygen-sensitive: exposure to oxygen can inhibit curing or polymerization via free radical scavenging, or induce oxidative degradation. In such cases, manipulation must be conducted under an inert gas atmosphere (e.g., argon). Additionally, resin solubility in the aqueous test medium must be considered; where necessary, stock solutions may first be prepared in a compatible organic solvent (e.g., dimethylsulfide) prior to the preparation of the test concentrations.

The concentration ranges tested in the ecotoxicity assays should be selected to enable determination of the median lethal concentration ( $LC_{50}$ ) or median effective concentration ( $EC_{50}$ ) for each resin in the target biological models, where feasible (noting that these parameters cannot be calculated if resins prove non-toxic).

For example, a stock solution of 34 mg/mL could be prepared by dissolving the resin in dimethyl sulfoxide (DMSO), ensuring the final solvent concentration does not exceed 0.01% (v/v) at the highest tested concentration. OECD guidelines recommend limiting solvent to  $\leq 0.01\%$  (100  $\mu$ L/L or 100 mg/L) as the solvent control threshold in standard assays with freshwater species (e.g., OECD TG 203, 236) to preclude confounding effects on survival, development, or behavior; higher levels (up to 1–2%) may be acceptable in specific cases, but require rigorous validation against solvent controls exhibiting  $\leq 10\%$  malformation or mortality.

The highest tested concentration of each resin does not need to surpass 100 mg/L, if no effects are observed. based on the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH).

## 5.2 Bio-based fibers and polymers in the form of pellets

For the bio-based fibers (carbon and wood) and polymers in the form of pellets (e.g., PLA, PA, and PCL), 24-h elutriates are prepared according to standard DIN 38414-4 in a 10:1 ratio (V:W), to simulate the potential release of substances and materials from solid matrices into aqueous phases.

The elutriates are prepared in distilled water and allowed to stir for a 24 h period at room temperature.

The elutriates obtain after 24 h are then filtered (0.22  $\mu\text{m}$  pore membrane) and afterwards supplemented with several salts, according to the requirements of each test medium, to avoid effects induced by osmotic stress in the tested biological models.

## 5.3 Intermediate composite formats

For the intermediate composite formats, leachates are prepared following the standard CEN/TS 15863, by using a liquid-to-surface area ratio of 8  $\text{cm}^3/\text{cm}^2$ .

These leachates are prepared by stirring the composite formats in distilled water for a 24 h period at room temperature, followed by filtration through 0.22- $\mu\text{m}$  pore-size membrane. The resulting leachates are then supplemented with several salts, according to the requirements of each test medium, to avoid any osmotic stress and effect in the biological models.

For the use in ecotoxicity assays, the pH and conductivity of the solutions elutriates and leachates (100% without salt supplementation, 100% with salts supplementation, and respective dilutions) shall be measured at the beginning of all assays. For algae and rotifers, due to a very low amount of volume of the suspensions and dilutions prepared these parameters may only be measured at the beginning of the assay.

## 6 Ecotoxicological assays

To account for varying chemical and material sensitivities among freshwater species, as well as their ecological relevance, the ecotoxicological assessment should employ monospecific bioassays with at least six representative freshwater taxa spanning key trophic and functional guilds, the following are suggested: two producers (*Raphidocelis subcapitata* and *Lemna minor*, the latter providing an additional uptake route and greater structural complexity); two primary consumers (*Brachionus calyciflorus* and *Daphnia magna*, representing small and large grazers, respectively); and two secondary consumers (embryonic stages of *Danio rerio* and *Xenopus laevis*). All assays should follow standardized guidelines (e.g., OECD, ISO). The following standard ecotoxicity assays as per OECD guidelines are recommend to be performed for the prepared solutions, elutriates and leachates.

### 6.1 72-h growth inhibition test *Raphidocelis subcapitata*

The growth inhibition assay with the freshwater microalgae *Raphidocelis subcapitata* should be conducted in accordance with the OECD Guideline 2011-201, adapted to 24-well microplate. The experiments shall begin with inocula from exponentially axenic growing cultures.

The control consist of MBL medium alone. A minimum of three replicates per control and tested concentration or dilution shall be performed, each should contain 1800  $\mu\text{L}$  of the solution, elutriate, or leachate desired or control medium (MBL), to which 200  $\mu\text{L}$  of microalgae inoculum (at an initial concentration of  $10^5$  algae cells  $\text{mL}^{-1}$ , to ensure that assays would begin with an initial algae concentration of  $10^4$  cells  $\text{mL}^{-1}$ ) must be added,

The test conditions shall be controlled ( $23 \pm 1$  °C of temperature and constant illumination of 100  $\mu\text{E m}^2 \text{ s}^{-1}$ ), and all wells shall be resuspended daily to prevent algal settling and shading.

To account for potential interference of the solutions, elutriates and leachates, additional wells of each solution, elutriate, and leachates dilution, without no algae, shall be conducted and exposed to identical conditions.

Cell density (CD, cells mL<sup>-1</sup>) is determined spectrophotometrically by measuring absorbance (ABS) at 440 nm. ABS values shall be corrected by subtracting readings from the corresponding blanks (for solution, elutriate, or leachate) and then converted to CD using a pre-established calibration curve (Annex A).

This must be curve prepared prior to the assays by quantifying microalgae cell concentrations (e.g., via Neubauer chamber counts) across a range of dilutions and measuring their corresponding absorbances at 440 nm.

The CD data is used to calculate *R. subcapitata* yield (Y, biomass produced during the assay, cells mL<sup>-1</sup>) and growth rate (*r*, day<sup>-1</sup>) for each solution, elutriate, leachate dilution treatment and control, as described in OECD Guideline 2011-201.

## **6.2 7-days *Lemna minor* Growth Inhibition test**

The 7-days *Lemna minor* growth inhibition assays should be performed by following the OECD guideline 2006-221. Three colonies with 4 fronds each of *L. minor* shall be exposed for 7 days to a control and to the range of concentrations or dilutions of the tested solutions, elutriates and leachates.

Three replicates shall be established for each treatment and the control, each replicate containing 8 mL of solution. The control consisted of Steinberg medium alone.

The test conditions shall be controlled ( $23 \pm 1$  °C of temperature and constant illumination of 100  $\mu\text{E m}^2 \text{s}^{-1}$ ).

At the end of the assay, the total number of fronds shall be recorded for yield determination (Y, based on the number of fronds) and the growth rate (*r*, day<sup>-1</sup>). The fronds fresh weight (mg) shall be assessed immediately, and the dry weight (mg) after lyophilization.

## **6.3 24-h acute test with *Brachionus calyciflorus***

The acute assay with the freshwater rotifer *Brachionus calyciflorus* should be performed according to the protocol acute Rotoxkit F (ROTOX-F), that conforms to ISO 19827:2015. ive replicates shall be assembled per treatment and control.

Each replicate shall contain 1 mL of each test solution, elutriate, or leachate or control medium (no food shall be added during the assay) and five newly hatched neonates shall be assigned per replicate.

After 24 h of incubation, at 23 °C in the dark, the number of dead rotifers shall be recorded

## **6.4 48-h Immobilisation test with *Daphnia magna***

The 48-h immobilisation test with the freshwater cladoceran *D. magna* shall be performed according to OECD guideline 2004- 202. In brief, neonates with less than 24-h old neonates, collected from 3<sup>rd</sup> to 5<sup>th</sup> broods, shall be exposed to a series of concentrations or dilutions .

Four replicates, each with 10 mL of test solution or dilution, shall be assembled by treatment or control, with five randomly assigned neonates. During the 48-h exposure, no food shall be added nor the medium renewed. The controls consists of standard ASTM hardwater alone.

Assays run under the controlled temperature of  $20 \pm 1$  °C and 16 hL: 8 hD photoperiod.

Mortality shall be checked at 24 and 48 h by gentle prodding of the organisms, considering it dead if no movement was observed within a 15-sec period.

## 6.5 96-h Fish Embryo Acute Toxicity test with *Danio rerio*

The 96-h Fish Embryo Acute Toxicity test with *D. rerio* should be performed accordingly to OECD guideline 2025-236. This test is recommended, instead of the juvenile OECD Test Guideline 203 (Fish, Acute Toxicity Test) to avoid conducting Animal experimentation (Directive 63/2010). The embryos used in the assays shall be collected within one hour after fish naturally mating and carefully screened under a stereomicroscope to discard injured and coagulated eggs. Before assigning the embryos to the assay, they shall be carefully washed twice with clean, sterilized maintenance water from the fish facility.

For the 96-h assay, ten embryos (~3 hours post-fertilization) shall be assigned per concentration or dilution and control. Assays shall be assembled in 24-well microplates, with one single egg assigned per well, filled with 2 mL of test solution or water, under controlled temperature and light conditions ( $26 \pm 1$  °C and 16 hL: 8 hD photoperiod). The control consists of zebrafish maintenance water solely (carbon filtered water at a conductivity of  $750 \pm 50$   $\mu\text{S}/\text{cm}$ ).

Every 24 h, mortality and the developmental stage of the embryos shall be recorded.

**Table 1 - Resume of the raw materials and formats and of the methods used to prepare the test solutions, elutriates, and leachates**

<b>Chemical/ Material group</b>		<b>Acronym</b>	<b>Methods for preparation of solutions or 24-h elutriates or 24-h leachates</b>
<b>Epoxy resins</b>	<b>Coatings</b>	Bisphenol-free diglycidyl ether of vanillyl alcohol ( <b>DGEVA</b> ) Phloroglucinol triglycidyl ether ( <b>PHTE</b> ) Diglycidyl ether of Bisphenol A* ( <b>DGEBA</b> ) 1,6-Hexanediamine* ( <b>1,6-H</b> ) 4,4'-Dithiodiamine* ( <b>4,4'-D</b> )	Stock solution of 34 mg/mL; Dimethyl sulfoxide as solvent (DMSO 0.3%), except for CYS and 1,6-H; dilution of the stock solution with the different test media
	<b>Hardener</b>	Cystamine ( <b>CYS</b> )	CYS and 1,6-H directly dissolved in the different test media
<b>Bio-based fibers</b>		Carbon fibers ( <b>CF</b> ) Wood fibers ( <b>WF</b> )	Standard DIN 38414-4 in a 10:1 ratio (V:W), filtered 0.22 µm pore membrane, supplemented afterwards
<b>Bio-based pellets</b>		Polyamide 10-10 ( <b>PA 10-10</b> ) Polylactic acid 1 ( <b>PLA1</b> ) Polylactic acid 2 ( <b>PLA2</b> ) Polylactic acid 3 ( <b>PLA3</b> ) Polylactic acid 4 ( <b>PLA4</b> ) Polycaprolactone ( <b>PCL</b> )	Standard DIN 38414-4 in a 10:1 ratio (V:W), filtered 0.22 µm pore membrane, supplemented afterwards
<b>Bio-based intermediate formats</b>	<b>Flax fibers reinforced</b>	BUP PRP04 BUP PRP05	Standard CEN/TS15863 in a proportion of 8 cm <sup>3</sup> cm <sup>-2</sup> , filtered 0.22 µm pore membrane, supplemented afterwards
	<b>Mono- and bicomponent filaments</b>	PLA 50216 PLA-PLA1-PLA2 (1- and 5-mm thickness) PLA-PLA3-PLA4 (3 mm thickness) PLA-PLA1-PLA4 (5 mm thickness)	
	<b>Bio-based thermoplastic material with carbon and wood reinforcement</b>	PA10 5% carbon PA10 5% wood	

**Annex A**  
(informative)

**Calibration curve**

*Concentration* (cells ml<sup>-1</sup>) = -17107.5 + (ABS × 7925350), where ABS is the absorbance at 440 nm.

Available at: Venâncio, C., Anselmo, E., Soares, A. and Lopes, I., 2017. Does increased salinity influence the competitive outcome of two producer species?. *Environmental Science and Pollution Research*, 24(6), pp.5888-5897. <https://doi.org/10.1007/s11356-016-8346-x>

## Bibliography

OECD (2011), Test No. 201: Freshwater Alga and Cyanobacteria, Growth Inhibition Test, OECD Guidelines for the Testing of Chemicals, Section 2, OECD Publishing, Paris, <https://doi.org/10.1787/9789264069923-en>

OECD (2006), Test No. 221: *Lemna* sp. Growth Inhibition Test, OECD Guidelines for the Testing of Chemicals, Section 2, OECD Publishing, Paris, <https://doi.org/10.1787/9789264016194-en>

OECD (2004), Test No. 202: *Daphnia* sp. Acute Immobilisation Test, OECD Guidelines for the Testing of Chemicals, Section 2, OECD Publishing, Paris, <https://doi.org/10.1787/9789264069947-en>

OECD (2025), Test No. 236: Fish Embryo Acute Toxicity (FET) Test, OECD Guidelines for the Testing of Chemicals, Section 2, OECD Publishing, Paris, <https://doi.org/10.1787/9789264203709-en>

Venâncio, C., Anselmo, E., Soares, A. and Lopes, I., 2017. Does increased salinity influence the competitive outcome of two producer species?. *Environmental Science and Pollution Research*, 24(6), pp.5888-5897. <https://doi.org/10.1007/s11356-016-8346-x>